















## SPECIFICATIONS

	<b>GEOLOGY</b>	Limestone
	<b>TYPE</b>	60% Bedface, 40% Splitface
	<b>PATTERN</b>	2:1 Sawn Course Heights   Dimensional Ashlar
	<b>HEIGHTS</b>	2-1/4" (20%), 5" (40%), 7-3/4" (30%), 10-1/2" (10%): Full Bed & Thin Veneer
	<b>LENGTHS</b>	8"-24" (Thin Veneer, crated/palletized material can exceed 20"); 8"-48" (Full Bed);
	<b>DEPTHS</b>	3/4" - 1 1/4" (Thin Veneer); 3"-5" Full Veneer)
	<b>COLORS</b>	Beige, Buff, Cream, Gray-Grey
	<b>COVERAGE</b>	Full Bed Depth Veneer: 35-40 Square Feet Per Ton
	<b>WEIGHT</b>	13.7 lbs. per square foot (Thin Veneer)
	<b>FLATS</b>	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f pallet, 180 s/f pallet
	<b>CORNERS</b>	10 l/f Box; 100 l/f Crate; 100 l/f pallet, Crated material can exceed 20"
	<b>NOTES</b>	Pre-packaged 60% Fond du Lac Dimensional, 40% Fond du Lac Clean-Split

### ASTM C-97

Water Absorption %	.31
Bulk Specific Gravity	2.83

### ASTM C-170

Parallel to Rift, Dry (psi)	36100
Parallel to Rift, Wet (psi)	32000
Perpendicular to Rift, Dry (psi)	35800
Perpendicular to Rift, Wet (psi)	30000

### ASTM C-99

Parallel to Rift, Dry (psi)	3770
Parallel to Rift, Wet (psi)	3500

### ASTM C-880

Perpendicular to Rift, Dry (psi)	1780
Perpendicular to Rift, Wet (psi)	1730



**GOLD QUARRY**  
 ANSI/NSC 373-2013  
 C0290908-101



**GOLD FABRICATOR**  
 ANSI/NSC 373-2013  
 C0289215-101