















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	100% Bedface
	PATTERN	2:1 Sawn Course Heights Dimensional Ashlar
	HEIGHTS	2-1/4" (20%), 5" (40%), 7-3/4" (30%), 10-1/2" (10%): Full Bed & Thin Veneer
	LENGTHS	Full Veneer: 8"-48" Thin Veneer: 6" - 20" (Crated or Palletized material can exceed 20")
	DEPTHS	3/4" - 1 1/4" (Thin Veneer); 3"-5" (Full Veneer)
	COLORS	Beige , Buff , Gray - Grey
	COVERAGE	Full Bed Depth Veneer: 35-40 Square Feet Per Ton
	WEIGHT	13.7 lbs. per square foot (Thin Veneer)
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f pallet, Crated material can exceed 20"
	NOTES	

ASTM C-97

Water Absorption %	.31
Bulk Specific Gravity	2.83

ASTM C-170

Parallel to Rift, Dry (psi)	36100
Parallel to Rift, Wet (psi)	32000
Perpendicular to Rift, Dry (psi)	35800
Perpendicular to Rift, Wet (psi)	30000

ASTM C-99

Parallel to Rift, Dry (psi)	3770
Parallel to Rift, Wet (psi)	3500

ASTM C-880

Perpendicular to Rift, Dry (psi)	1780
Perpendicular to Rift, Wet (psi)	1730



GOLD QUARRY
 ANSI/NSC 373-2013
 C0290908-101



GOLD FABRICATOR
 ANSI/NSC 373-2013
 C0289215-101