















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	70% Splitface (Fond du Lac Country), 30% Bedface (Fond du Lac Manor)
	PATTERN	Natural Course Heights 2:1 Random Ashlar
	HEIGHTS	Varies from 2" - 9" (Full Bed); 2" - 6" (Thin Veneer)
	LENGTHS	Random, from 8" - 36" (Full Bed); 8" - 24" (Thin Veneer, crated/palletized material can exceed 20")
	DEPTHS	3/4" - 1 1/4" (Thin Veneer); 3"-5" Full Veneer
	COLORS	Buff, Gray-Grey
	COVERAGE	Full Bed Depth Veneer: 35-40 Square Feet Per Ton
	WEIGHT	14.9 lbs. per square foot (Thin Veneer)
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f pallet
	NOTES	Formerly NSVI's "Arlington"; pre-packaged 70% Splitface (FDL Country), 30% Bedface (FDL Manor)

ASTM C-97

Water Absorption %	.31
Bulk Specific Gravity	2.83

ASTM C-170

Parallel to Rift, Dry (psi)	36100
Parallel to Rift, Wet (psi)	32000
Perpendicular to Rift, Dry (psi)	35800
Perpendicular to Rift, Wet (psi)	30000

ASTM C-99

Parallel to Rift, Dry (psi)	3770
Parallel to Rift, Wet (psi)	3500

ASTM C-880

Perpendicular to Rift, Dry (psi)	1780
Perpendicular to Rift, Wet (psi)	1730



GOLD QUARRY
 ANSI/NSC 373-2013
 C0290908-101



GOLD FABRICATOR
 ANSI/NSC 373-2013
 C0289215-101